



Received: 12/14/2015 Completed: 12/15/2015 Letter: P JB P.O.#: Test Report #: 3-10912-0-

Client's Identification Style: Duratex 8oz Black Back Mesh Banner. Width: 38". Finish: Matte. Weight: 8oz. End Use: Display Media.

Tested For: **Rob Pinedo** Key Test: NFPA 701-2015 TM#2 Flat 445  
 Pitman Co./Agfa Graphics  
 21908 E. Valley Blvd Tel: 1-(800)-526-5441 Ext: 2896  
 City of Industry, CA 91789 Fax: 1-(909)-595-1451

LE:2015 NE:2019 V:01/15 PC:1H  
 TEST PERFORMED: NFPA 701 - Standard Methods of Fire Tests for Flame Propagation of Textiles and Films - 2015 Edition - Test Method #2 - Flat Sheet Specimens

SPECIMEN CONFIGURATION:  Single Layer;  Multi Layer

RESULTS REPORTED:  Initially  After 72 hours water leaching  
 After 3 dry cleanings  After 100 hours accelerated weathering  
 After 5 launderings @ 160°F

RESULTS:

Length Specimen #	Afterflame (seconds)	Drip Burn (seconds)	Char Length (mm)
1	0	0	130
2	0	0	146
3	0	0	118
4	0	0	135
5	0	0	148
6	0	0	150
7	0	0	129
8	0	0	145
9	0	0	150
10	0	0	139

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 267 g/m²

FAILURE CRITERIA: For each individual specimen --

Afterflame	Drip Burn	Char Length
Exceeds 2.0 seconds	Exceeds 2.0 seconds	Exceeds 435 mm (17.1")

RETEST PROVISION: Test 5 additional specimens if only 1 specimen fails.

CONCLUSION: Based on the above Results and Failure Criteria, the item tested:  
 Passes;  Fails;  Requires testing of 5 additional specimens



96-D Allen Boulevard  
 Farmingdale, New York 11735-5626 USA  
 Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956  
 e-mail: testing@govmark.com

Received: 12/14/2015	Completed: 12/15/2015	Letter: P	JB	P.O.#:	Test Report #:	3-10912-0-
Client's Identification	Style: Duratex 8oz Black Back Mesh Banner. Width: 38". Finish: Matte. Weight: 8oz. End Use: Display Media.					
Tested For: <b>Rob Pinedo</b>			Key Test: NFPA 701-2015 TM#2 Flat			445
Pitman Co./Agfa Graphics 21908 E. Valley Blvd City of Industry, CA 91789			Tel: 1-(800)-526-5441		Ext: 2896	
			Fax: 1-(909)-595-1451			


PRECONDITIONING:     1 hr @ 220°F (Standard)  
                            24 hrs @ 68±9°F (Alternate: Material shrinks/distorts @ 220°F)

REMARKS: None.

CONVERSION FACTORS:

mm ÷ 25.4 = inches  
 g/m<sup>2</sup> ÷ 28.35 x .835 = oz/yd<sup>2</sup>

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by NFPA 701 - 2015 Edition Test Method #2 Flat Sheet Specimens.

  
 -----  
 AUTHORIZED SIGNATURE  
 GOVMARK  
 /ec /bg

**MS. PHYLLIS PETTIT**

**DEC 17 2015**